



CHEMSHUN CERAMICS-- Epoxy Resin Adhesive

No.	Attributes	Unit	Type -1	Type -2	Type -3
1	Color	-	White	White	Red
2	Density	g/cc	1.28	1.24	1.20
3	Shear strength	Mpa	25.20	23	≥2.0
4	Tensile strength	Mpa	65	35	≥2.0
5	Condition of cure	25°C,h	24	24	24
6	Working temperature	°C	-60~150	-60~200	200~300
7	Matching (A:B)		4:1	4:1	4:1

• Usage Method

• d and Attentions

1. All loose rust and soot, oil, grease or any loose particles must be removed by angle grinder from the surface of the areas on which ceramic tiles is to be applied.
2. The adhesive includes two parts A and B. Part A and Part B mixed as per the matching 4:1 together to be the same color. and put them on the steel surface.
3. The mixed adhesive must be used up within 30 minutes under 25°C temperature condition. (So, do not mix too much every time).
4. To avoid contact with the skin, eyes, and inadvertently adhere to the skin, can be used alcohol or soap to clean, and then wash clean. Such as accidentally into eyes, immediately rinse with clear water and go to a doctor immediately.
5. The condition of cure is 24hours, it means that only after 24hours later, the equipment of engineering with ceramic lied could to be application.

•Package

- First Packing; small plastic drum, A=4kgs, B=1kgs and then total 20kgs for a box.
- Keep stock in cool ventilated place, storage period is two years. More than the shelf life of the appropriate viscosity can still be used, does not affect the results.
- The product is a non-dangerous goods, according to the general chemical transport.

Pingxiang Chemshun Ceramics Co.,Ltd

In English

En español



Address: Non-metal area of shangliuyuan, Economic developmentzone,
pingxiang city, Jiangxi province, P.R.China.
Website: www.chemshun.com www.chemshun-es.com